

# ABS Resin

Model: MX-50

Analysis Mode:

Automatic mode

(Termination value: 0.005%/min)

Weight 10g

Temperature 140C


Analysis Time 12.1min

Moisture Content

Mean Value 0.425%

Repeatability 0.0093%

CV Value 2.19%



1st 0.43%

2nd 0.41%

3rd 0.43%

4th 0.43%

Remarks:

Average Moisture Content

0.271%

Repeatability

0.0177%

Average Analysis Time

15.7min

At 140C with 0.2g by

Karl Fischer method.