

# Synthetic Resin Paint

(Acrylic and Aqueous Fluid Type)

Model: MX-50

Analysis Mode:

Standard mode

(Accuracy: MID)

Weight 1g

Temperature 200C

Analysis Time 13.6min

Moisture Content

Mean Value 53.93%

Repeatability 0.150%

CV Value 0.28%

1st 53.83%

2nd 54.10%

3rd 53.85%

Remarks:

Use a grass fiber sheet.

