


Polyethylene Terephthalate Pellet

Model: MX-50
Analysis Mode:
Standard mode
(Accuracy: HI)
Weight 10g
Temperature 180C
Analysis Time 6.8min
Moisture Content
Mean Value 0.298%
Repeatability 0.0045%
CV Value 1.34%



Remarks:
Average Moisture Content
0.307%
Repeatability
0.0045%
Average Analysis Time
19.0 min
At 180C with 0.3g by
Karl Fischer method.